














Nylon 6, textured, semi-dull, yarn-dyed

What it is


It's a synthetic fiber, **polycaprolactam**, derived from chemicals (petroleum) that is made spinnable through synthesis processes and transformed into textile yarns.



Performances

 Melting point °C	215 °C
 Softening point °C	180 °C
 Ironing temperature °C	150 °C
 Humidity rate 65 RH% - 20 °C	4,50
TC Conventional rate (Bisfa)%	5,75 %
 Specific weight	1,14 gr/cm ³
 Resistance to sunlight	■ ■ □ □
 Stain resistance	■ ■ □ □
 Resistance to organic solvents - dry cleaning	■ ■ ■ □
 Wear resistance	■ ■ ■ □
 Dimensional washing stability	■ ■ ■ □
 Rapidity of drying	■ ■ ■ □
 Moisture absorption / breathability	■ ■ □ □

End uses



Dyed with acid, premetallized, or dispersed colorants.

Available in stock service



Dtex	Fil	Ply	Tpm	Colors	Cone weight (kg)	N° cones per box	Box weight (kg)
33	10	2	150 "S"	Color card 101	0,50	44	22
44	13	2	100 "S"	Color card 101	1,20	22	25
78	24	1	"S"	Black & White	1,20	22	25
78	24	2 or 3	100 "S"	Color card 101	1,20	22	25

Available on demand

78	24	1	"S"	Color card 101	1,20	22	25
78	18	2	Mélange	Specific card	1,20	22	25
78	24	4	100 "S"	Color card 101	1,20	22	25
78	68	2	IMG or 100 "S"	Color card 101	1,20	22	25

The weights of the packages and boxes are indicative and may be subject to change due to production needs.